

**Materialprüfungsanstalt
Universität Stuttgart**
P.O. Box 80 11 40
70511 Stuttgart
Germany

MPA **MPA STUTTGART**
Otto-Graf-Institut
Materialprüfungsanstalt Universität Stuttgart



Test Report

Client: Loba GmbH & Co. KG
Leonberger Str. 56-62
71254 Ditzingen

Order-No. (Client):

Order-No. (MPA): **L 902 6970 000 Whr/Sc (901 2649-3 Kf/Sc)**

Test Item: **LOBADUR and LOBACARE on parquet“**

Specification Applied: DIN V 18032-2:2001-04

Date of Receipt of Test Item 2006

Date of Test: 2006

Date of Report: 07.11.2013

Page 1 of 2 text pages

Enclosures :

Supplements:

Total Number of Pages: 2

Number of Reports: 1

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.

In compliance with DIN EN ISO/IEC 17025 accredited Testing Laboratory recognized by DAkkS Deutsche Akkreditierungsstelle GmbH.
Accreditation valid for testing methods listed in the certificates (Reg. No. D-PL-11016-00).

1 Purpose of investigation

You commissioned us to test the sliding properties according to DIN V 18032-2:2001-04 of a parquet floor sample that was sent to us and labeled as follows:

Lacquer: 1 x approx.: 80 g/m² **LOBADUR WS EasyPrime**
Lacquer: 2 x approx.: 120 g/m² **LOBADUR WS EasyFinish**
Maintenance: maintained with **LOBACARE SPORTCARE**

2 Testing procedure

The test was carried out according DIN V 18032-2:2001-04.

The procedure applied is accredited according to DIN EN ISO/IEC 17025:2005 (DAkks-registration-no. D-PL-11016-01-09).

Testing conditions: 23-50-2 according to DIN 50014.

3 Test results

The following test results were obtained.

Table 1: Test results:


testing spot no.	sliding coefficient μ
1	0,44
2	0,45
3	0,40
4	0,43
5	0,43

4 Evaluation

According to DIN V 18032-2:2001-04 the following requirement is valid: μ min. 0,4, μ max. 0,6.


This requirement was fulfilled by the above described sample.

Prepared by


Johannes Schmid
Tester



Approved and released by


Dipl.-Ing. Rainer Wellhäußer
Vice Section leader